## SOLIBRO SL2 CIGS THIN-FILM MODULE



Solibro's SL2 thin-film modules offer efficiencies up to 13.2 % in serial production. The modules are especially suited for roof-parallel installations on flat rooftops. This allows minimal shadowing with maximal energy yield. Due to their frameless design, SL2 modules possess excellent self-cleaning properties and require minimal maintenance. All SL2 modules are "Made in Germany" and are tested according to very high standards in order to insure a long lifetime and stable module performance.



## MAXIMIZE YOUR ENERGY YIELD

Additional power through positive lightsoaking: In contrast to ordinary solar cells, our CIGS modules increase in power under illumination. Combined with our strict positive sorting, you get up to 15 % more power for your money.

**Our modules deliver top performance even at very high temperatures:** With a temperature coefficient of -0.38 %/K, the Solibro CIGS modules are a long way ahead of their crystalline competitors, producing high yields even under critical climatic conditions.

**Excellent usage of sunlight:** Our modules allow PV installations regardless of whether the roof faces to the south, east or west. SL2 modules generate high energy yields even when installed parallel to the roof.

## **ONE MORE ADVANTAGE FOR YOU**

Aesthetic appearance: The uniformly black SL2 solar modules are ideal for architecturally demanding photovoltaic installations.

**Controlled quality:** Solibro's SL2 modules are certified according to IEC 61646, IEC 61730 and UL 1703. A multitude of additional quality checks ensure that each single module fulfills the same high standards guaranteeing your long-term energy yields.



MECHANICAL S	PECIFICATION	TECHNICAL DRAWING				
Length	1190 (+3/-1) mm	, <u>1190 - 1</u>				
Width	789.5 (+3/-1) mm					
Height	7.3 mm (+ Junction box, 15 mm)	<b>↓</b>				
Weight	16.5 kg					
Front cover	4 mm tempered low iron glass (ESG)					
Back cover	3 mm float glass					
Frame	None	**************************************				
Cell type	CIGS [Cu(In, Ga) Se <sub>2</sub> ]					
Junction box	Protection class IP 65, with 1 bypass diode (3A) 66 x 54 x 15 mm <sup>3</sup>	Anschlussdose	-			
Cable type	Solar cable 2.5 mm <sup>2</sup> ; (+) 855 (+30/-0) mm; (-) 735 (+30/-0) mm	Produktlabel				
Connector	MC4					

ELECTRICAL CHARACTERISTICS

PERFORMANCE AT STANDARD TEST CONDITIONS (STC: 1000 W/m2, 25 °C, AM 1.5 G SPECTRUM) <sup>1</sup>							
POWER CLASS (+5/-0 W)		[W]	100	105	110	115	120
Minimum Power	P <sub>MPP</sub>	[W]	100.0	105.0	110.0	115.0	120,0
Short Circuit Current	Isc	[A]	1.68	1.68	1.69	1.69	1.69
Open Circuit Voltage	U <sub>oc</sub>	[V]	90.1	91.6	93.3	95.1	97.6
Current at P <sub>MPP</sub>	I <sub>MPP</sub>	[A]	1.46	1.49	1.52	1.54	1.56
Voltage at P <sub>MPP</sub>	U <sub>MPP</sub>	[V]	68.5	70.5	72.4	74.7	76.9
Nominal efficiency	η	[%]	≥10.6	≥11.2	≥11.7	≥12.2	≥12.8
PERFORMANCE AT NORMAL OPERATING CELL TEMPERATURE (NOCT: 800 W/M2, 51 $\pm$ 2 °C, AM 1.5 G SPECTRUM) <sup>1</sup>							
POWER CLASS (+5/-0 W)		[W]	100	105	110	115	120
Minimum Power	P <sub>MPP</sub>	[W]	72.3	75.9	79.5	83.1	86.7
Short Circuit Current	Isc	[A]	1.34	1.34	1.35	1.35	1.35
Open Circuit Voltage	U <sub>oc</sub>	[V]	82.0	83.4	84.9	86.5	88.8
Current at P <sub>MPP</sub>	I <sub>MPP</sub>	[A]	1.16	1.18	1.21	1.22	1.24
Voltage at P <sub>MPP</sub>	U <sub>MPP</sub>	[V]	62.1	64.0	65.7	67.8	69.8

<sup>1</sup> Measurement accuracy PMPP: ± 5 %; measurement accuracy ISC, VOC, IMPP, VMPP: ± 10 %. All STC measurements are based on a pre-treatement of modules with 43 kWh/m<sup>2</sup> of light soaking (43 hours at 1000 W/m<sup>2</sup> and MPP) followed by a cool down to 25 °C. For system conception, please take into account the typical relative VOC and VMPP power increase of 2.5 % after 215 kWh/m<sup>2</sup> of light soaking. This power boost is not included in the nominal values of this data sheet.

TEMPERATURE COEFFICIENTS (AT 1000 W/M2, AM 1.5 G SPECTRUM)

Temperature Coefficient of I <sub>sc</sub>	α	[%/K]	+ 0.00 ± 0.04	Temperature Coefficient of U <sub>oc</sub>	β	[%/K]	-0.29 ±0.04	
Temperature Coefficient of P <sub>MPP</sub>	Y	[%/K]	$-0.38 \pm 0.04$					
I-V CURVES AT VARIOUS TEMPERATURES AND IRRADIANCE LEVELS				PERFORMANCE AT LOW IRRADIANCE				





The typical relative change in module efficiency (at nominal power) at an irradiance of 200 W/m<sup>2</sup> in relation to 1000 W/m<sup>2</sup> (both at 25 °C and AM 1.5 G spectrum) is -4.0 % rel.

PROPERTIES FOR SYSTEM DES	GN		QUALIFICATIONS AND CERTIFICATES			
Maximum System Voltage V <sub>sys</sub>	[ <b>V</b> ] 1000 (IE	C) / 600 (UL 1703)	IEC 61646 (Ed. 2), IEC 61730 (Ed.1) application class A, UL 1703 The production site is certified according to ISO 9001 for Quality Management			
Maximum Reverse Current $I_{\scriptscriptstyle R}$	[ <b>A</b> ] 4					
Wind / Snow Load	[Pa] 2400					
Safety Class	11					
Fire Rating	С		Safety Class II C Zertifiziert US UL 1703			
Permitted module temperature on -40 °C bis +85 °C continous duty		°C	The content of this data sheet is according to DIN EN 50380.			

Note: See the installation and operating manual or contact the technical service for further information on approved installation and use of this product.

## SOLIBRO GMBH

OT Thalheim, Sonnenallee 32-36 06766 Bitterfeld-Wolfen, Germany PHONE +49(0)3494 3840 - 93000 EMAIL sales@solibro-solar.com FAX +49(0)3494 3840 - 93100

WEB www.solibro-solar.com

